

Technical Data Sheet

AMPCO[®] 18

Centrifugal Castings



Nominal composition:

Aluminium	(Al)	10.5%
Iron	(Fe)	3.5%
Others		max. 0.5%
Copper	(Cu)	balance

Mechanical and physical properties	Units	Nominal Values
Tensile strength R_m	KSI	105
Yield strength $R_{p 0.5}$	KSI	41
Elongation in 2"	%	18
Brinell hardness	BHN 30	183
Rockwell hardness	HRB	90
Reduction of area ψ	%	20
Compressive strength ultimate R_{mc}	KSI	139
Proportional limit in compression R_{pc}	KSI	30
Shear strength R_{cm}	KSI	58
Modulus of elasticity E (tension)	KSI	16000
Charpy a_K keyhole	FT.LBS	14
Izod a_K	FT:LBS	20
Fatigue (100'000'000 cycles) σ_N	KSI	33
Density ρ	LBS / IN ³	0.269
Coefficient of expansion α	IN / IN / °F	$9 \cdot 10^{-6}$
Thermal conductivity λ	CGS	0.15
Electrical resistivity γ (1mm ² section)	Microhms/ Meter	125
Electrical conductivity	% I.A.C.S.	14
Specific heat c_p	BTU / LB · °F	0.1

Assurances given with respect to properties or uses are subject to written approval from AMPCO METAL.

The exceptional wear and fatigue resistance of this alloy results from a controlled duplex alpha and beta phase. This alloy has high strength combined with good ductility and unusual toughness.

The physical characteristics of this alloy can be varied by heat treatments (AMPCO[®] 18.22, 18.23 and 18.136).

APPLICATIONS:

This alloy is well suited for use as gears, worm wheels, bushings and bearings.

The machine tool industry has adopted AMPCO[®] 18 as standard for all applications requiring good sliding properties, wear resistance, fatigue resistance, toughness and/or resistance to deformation under load.

AMPCO[®] 18 is used in steel mill service as screw down nuts, slippers (many of which are "cast to size"), gears, wedges and breaker blocks. AMPCO[®] 18 has an excellent corrosion resistance and is used in pickling service for such parts as hooks, crates and spreaders, etc.

AMPCO METAL EXCELLENCE IN ENGINEERED ALLOYS

info@ampcometal.com

www.ampcometal.com