

Technical Data Sheet

AMPCO[®] 22

Centrifugal Castings

Nominal composition:

Aluminium	(Al)	14.1%
Iron	(Fe)	4.7%
Others		max. 0.5%
Copper	(Cu)	balance

Mechanical and physical properties	Units	Nominal Values
Tensile strength R_m	MPa	586
Yield strength $R_{p0.2}$	MPa	489
Elongation A_5	%	0.5
Brinell hardness	HBW 10/3000	331
Rockwell hardness	HRC	35
Reduction of area ψ	%	0
Compressive strength R_{mc}	MPa	1448
Compressive strength, 0.1 % perm. set	MPa	655
Shear strength R_{cm}	MPa	483
Modulus of elasticity E	GPa	103
Charpy a_K	J	2.7
Izod a_K	J	2.7
Density ρ	g / cm ³	7.06
Coefficient of expansion α	10 ⁻⁶ / K	16.2
Thermal conductivity λ	W / m · K	42
Electrical conductivity γ	m / Ω · mm ²	6
Electrical conductivity	% I.A.C.S.	10
Specific heat c_p	J / g · K	0.42

Assurances given with respect to properties or uses are subject to written approval from AMPCO METAL.

AMPCO[®] 22 is a duplex structure alloy of approx. 50 % of each phase - gamma 2 and beta. It is remarkable because of its hardness, its excellent compression and wear resistance and by its sliding properties.

As the elongation of the material is very low, thin sections should be avoided and the material should be well backed up.

APPLICATIONS:

The field of service of AMPCO[®] 22, with few exceptions, is limited to forming and/or drawing stainless steel, especially when runs are long or gauge is heavy and it is essential that tolerances are maintained.