

# Technical Data Sheet

## AMPCO<sup>®</sup> M4

### Centrifugal Castings



#### Nominal composition:

|           |      |           |
|-----------|------|-----------|
| Aluminium | (Al) | 10.5%     |
| Iron      | (Fe) | 4.8%      |
| Nickel    | (Ni) | 5.0%      |
| Manganese | (Mn) | 1.5%      |
| Others    |      | max. 0.5% |
| Copper    | (Cu) | balance   |

| Mechanical and physical properties                         | Units                 | Nominal Values    |
|--|-----------------------|-------------------|
| Tensile strength $R_m$                                     | KSI                   | 135               |
| Yield strength $R_{p 0.5}$                                 | KSI                   | 105               |
| Elongation in 2"   | %                     | 6                 |
| Brinell hardness   | BHN 30                | 293               |
| Rockwell hardness  | HRC                   | 30                |
| Reduction of area $\psi$                                   | %                     | 5                 |
| Compressive strength $R_{mc}$                              | KSI                   | 180               |
| Compressive strength, 0.1 % perm. set                      | KSI                   | 110               |
| Shear strength $R_{cm}$                                    | KSI                   | 80                |
| Modulus of elasticity E                                    | KSI                   | 18000             |
| Charpy $a_K$   | LBS.FT                | 5                 |
| Fatigue (100'000'000 cycles) $\sigma_N$                    | KSI                   | 37                |
| Density $\rho$   | LBS / IN <sup>3</sup> | 0.269             |
| Coefficient of expansion $\alpha$                          | IN / IN / °F          | $9 \cdot 10^{-6}$ |
| Thermal conductivity $\lambda$                             | CGS                   | 0.1               |
| Electrical resistivity $\gamma$ (1mm <sup>2</sup> section) | Microhms/ m           | 208               |
| Electrical conductivity                                    | % I.A.C.S.            | 8.2               |
| Specific heat $c_p$  | BTU / LB. °F          | 0.107             |

Assurances given with respect to properties or uses are subject to written approval from AMPCO METAL.

The patented process gives AMPCO<sup>®</sup> M4 mechanical properties beyond the range of commercial nickel-aluminium bronzes, comparable to beryllium copper at a lower cost and without the beryllium copper industrial hygiene requirements.

#### APPLICATIONS:

AMPCO<sup>®</sup> M4 was initially developed as an aircraft specification alloy for gears in retractable landing assemblies, engine spacer bearings and other similar applications. It is rapidly growing in use where higher mechanical properties at elevated temperatures together with corrosion-resistant properties are required.

Typical applications include aircraft landing gear bearings and bushings, bending dies (shoes and mandrels) for the tube bending industry, gear wheels and wear/guide plates, etc..

#### Specification: AMS 4881 for castings

**AMPCO METAL EXCELLENCE IN ENGINEERED ALLOYS**

info@ampcometal.com

www.ampcometal.com