



Technical Data Sheet

AMPCOLOY® 944

AMPCOLOY® 944 is designed to provide excellent thermal conductivity, high tensile strength, and hardness while eliminating the need for beryllium. This high copper alloy provides the essential properties required for demanding industrial tasks, making it a reliable and safe choice for applications that require both high mechanical performance and compliance with health and safety regulations.

Key Features:

- ▶ High tensile strength & hardness
- ▶ Good thermal & electrical conductivity
- ▶ Beryllium-free
- ▶ Safe alternative to Beryllium Copper
- ▶ Food certified by ISEGA
- ▶ Corrosion & wear resistant
- ▶ RWMA Class 4
- ▶ Increasing conductivity at higher temperatures



Nominal Composition:

Copper (Cu)	Nickel (Ni)	Silicon (Si)	Chromium (Cr)	Others
Balance	7.0%	2.0%	1.0%	max. 0.5%

Applications:

- ▶ Safe alternative to Beryllium Copper
- ▶ Used to comply with strict health and safety regulations
- ▶ Injection molding, thermoforming & blow molding
- ▶ Electrode holders, spot-welding electrodes & seam welding discs
- ▶ Projection & butt-welding dies
- ▶ Plunger tips for cold-chamber aluminum high-pressure die casting
- ▶ Molds for low-pressure die casting



AMPCOLOY® 944 has a wide range of applications in various industries where a combination of excellent electrical and thermal conductivity, high mechanical properties, and safety compliance is essential. This versatile alloy is used for plastic molding, resistance welding and die casting as well as in general engineering, automotive, metal processing, oil, gas & chemical industries.



Technical Data Sheet

AMPCOLOY® 944

Mechanical Properties (Nominal values)	Forged	Extruded
Tensile Strength R_m (MPa)	793	938
Yield Strength $R_{p0.5}$ (MPa)	655	730
Elongation A_5 (%)	4	5
Brinell Hardness (10/3000)	270	294
Compressive Yield Strength $R_{pc0.1}$ (MPa)	700	710
Charpy a_k (J)	8	7
Modulus of Elasticity E (GPa)	135	151

Physical Properties:

Density ρ (g/cm ³)	Coefficient of Expansion α (10 ⁻⁶ /K)	Thermal Conductivity λ (W/m·K)			Electrical Conductivity γ (m/Ω·mm ²)	Electrical Conductivity (% I.A.C.S.)	Specific Heat c_p (J/g·K)
8.69	17.5	20°C 156	100°C 170	200°C 190	17.4	30	0.38

Machining Parameters:

Operation	Cutting Speed v_c (m/min)	Feed f (mm/rev)	Depth a (mm)	Tool Specification
Milling – Roughing	160 - 240	0.1 - 0.2	up to 2	K10 - K20
Milling – Finishing	180 - 250	0.05 - 0.1	0.1 - 0.2	K10 - K20
Turning – Roughing	160 - 240	0.1 - 0.2	up to 2	K10 - K20
Turning – Finishing	180 - 250	0.05 - 0.1	0.1 - 0.2	K10 - K20

Scan the QR Code to view our machining recommendations:



Contact us

