

## AMPCOLOY® 940 and AMPCOLOY® 944

### Machining Recommendations (English imperial)

#### Turning

	Carbide Insertable or Solid Carbide	Roughing	Finishing
AMPCOLOY® 940	Cutting speed (feet/min)	400 - 800	500 - 1000
	Feed (inches <sup>-1</sup> )	0,006 - 0,012	0,002 - 0,004
	Depth of cut (inches)	- 0,14	0,01 - 0,02
AMPCOLOY® 944	Cutting speed (feet/min)	400 - 1000	400 - 1300
	Feed (inches <sup>-1</sup> )	0,006 - 0,012	0,002 - 0,004
	Depth of cut (inches)	- 0,16	0,01 - 0,02

#### Face Milling

	Carbide Insertable or Solid Carbide	Roughing	Finishing
AMPCOLOY® 940	Cutting speed (feet/min)	650 - 1300	2000 - 3600
	Feed (inches/tooth)	0,004 - 0,015	0,004 - 0,008
	Depth of cut (inches)	- 0,2	0,004 - 0,02
AMPCOLOY® 944	Cutting speed (feet/min)	600 - 650	1650 - 2600
	Feed (inches/tooth)	0,004 - 0,015	0,004 - 0,008
	Depth of cut (inches)	- 0,12	0,004 - 0,02

#### Plain Milling

	Carbide Insertable or Solid Carbide	Roughing	Finishing
AMPCOLOY® 940	Cutting speed (feet/min)	300 - 650	650 - 800
	Feed (inches/tooth)	0,004 - 0,012	0,002 - 0,005
	Depth of cut (inches)	Up to mill • Φ	0,004 - 0,012
AMPCOLOY® 944	Cutting speed (feet /min)	250 - 650	600 - 800
	Feed (inches/tooth)	0,008 - 0,015	0,002 - 0,006
	Depth of cut (inches)	Up to mill • Φ	0,002 - 0,012

#### Drilling and Tapping

		Drilling	Tapping
		Solid Carbide (w. internal cooling)	HSS
AMPCOLOY® 940	Cutting speed (feet/min)	250 - 400	25 - 40
	Feed (inches)	0,002 - 0,006	
AMPCOLOY® 944	Cutting speed (feet/min)	250 - 400	25 - 40
	Feed (inches)	0,003 - 0,008	